

Appendix 9.

Specifications for Apparatus and Containers/Packages
made of Glass, Ceramic, or Enamel

Elution Tests

Test method		Specification		
Elution condition	Analytical method	Type of ware	Lead	Cadmium
1. <i>Solvent</i> 4% Acetic acid. 2. <i>Temperature</i> Room temperature. 3. <i>Time</i> 24hours. 4. <i>Room condition</i> Dark place	Atomic absorption spectrometry	Flat-ware (with the depth of less than 25mm)	Not more than 17 μ g/cm ²	Not more than 1.7 μ g/cm ²
		Hollow-ware (with the depth of 25 mm or more) <ul style="list-style-type: none"> • The capacity of 1.1L or more • The capacity of less than 1.1L 	Not more than 2.5 ppm Not more than 5 ppm	Not more than 0.25 ppm Not more than 0.5 ppm